

Seawater RO Elements

Туре	Diameter Inch	Membrane Area ft²(m²)	Salt Reje %	ection	Product Flow Rate gpd(m³ / d)	Feed Spacer Thickness mil
TM840M-1760	16"	1,760(164)	99.8	}	30,800(117)	28
TM840V-1760	16"	1,760(164)	99.8	3	39,600(150)	28
1. Membrane Type				Cross Li	nked Fully Aromatic Polyami	de Composite
2. Test Conditions						
	F	eed Water Pressure		800 ps	si(5.52MPa)	
	F	eed Water Temperature		77° F	(25°C)	
	F	eed Water Concentration		32,000) mg/l Nacl	
	F	Recovery Rate		8%		
	l _F	eed Water pH		7		


99.5%

4. Minimum Product Flow Rate 24,600gpd(93m³/d) (TM840M-1760) 31,700gpd(120m³/d) (TM840V-1760)

5. Boron Rejection 95% at pH8 (TM840M-1760) (typical value) 92% at pH8 (TM840V-1760) (5mg/l Boron added to Feed water)

Dimensions

3. Minimum Salt Rejection



Operating Limits

	1200psi (8.3 MPa) 113° F (45°C)
Maximum Feed Water SDI15	5
Feed Water Chlorine Concentration	Not detectable
Feed Water pH Range, Continuous Operation	2-11
Feed Water pH Range, Chemical Cleaning —————	1-12
Maximum Pressure Drop per Element —	15 psi (0.10 MPa)
Maximum Pressure Drop per Vessel ——————————————————————————————————	50 psi (0.34 MPa)

Operating Information

- 1. For the recommended design range, please consult the latest Toray technical bulletin, design guidelines, computer design program, and/ or call an application specialist. If the operating limits given in this Product Information Bulletin are not strictly followed, the Limited Warranty will be null and void.
- 2. All elements are wet tested, treated with tested feed water solution, and then vacuum packed in oxygen barrier bags with deoxidant inside. To prevent biological growth during system shutdown, it is recommended to perform 30-60 minutes flushing of Toray elements with seawater once in every two days.
- 3. The presence of free chlorine and other oxidizing agents under certain conditions, such as heavy metals which acts as oxidation catalyst in the feed water will cause unexpected oxidation of the membrane. It is strongly recommended to remove these oxidizing agents contained in feed water before operating RO system.
- 4. Permeate from the first hour of operation shall be discarded.
- 5. The customer is fully responsible for the effects of chemicals that are incompatible with the elements. Their use will void the element Limited Warranty.

Notice

- 1. Toray accepts no responsibility for results obtained by the application of this information or the safety or suitability of Toray's products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product combination for their own purposes.
- 2. All data may change without prior notice, due to technical modifications or production changes.

Asia and Oceania: Toray Industries, Inc. RO Membrane Products Department

1-1 Nihonbashi muromachi 2-chome Chuo-ku, Tokyo 103-8666, Japan Tel: +81 3 3245 4540 Fax: +81 3 3245 4913

http://www.toraywater.com

Americas: Toray Membrane USA, Inc. Sales Office

13435 Danielson St Poway, CA 92064, USA Tel: +1 858 218 2390 Fax: +1 858 486 3063

Europe, Middle East and Africa: Toray Membrane Europe AG

Grabenackerstrasse 8 CH-4142 Münchenstein 1, Switzerland Tel: +41 61 415 87 10 Fax: +41 61 415 87 20

Toray BlueStar Membrane Co., Ltd.

No.5 Anxiang Street, Area B, Beijing Tianzhu Airport Economic Development Zone, Beijing ,101318 P.R.C. Tel: +86 10 80490552 Fax: +86 10 80485217